

Paragliders Shock- and sustained loading test

Inspection certificat number: **PG_1318.2018**

Test Report

Manufacturer data

Manufacturer name: **MCC Aviation SA**
 Representative: **Alexandre Paux**
 Street: **Route de Forel 34 - La Tuilière**
 Post code / place: **1091 Grandvaux**
 Country: **Switzerland**

Sample data

Name: **Stelvia**
 Size: **L**
 Maximum weight in flight [kg]: **115**
 Serial number: **2018-03-31-0604**
 Date of reception: **08.03.2018**

Test data


Test Atmosphere AGL

Place of test:	Yverdon (airport)	6.7	[°C]
Date of test:	09.03.2018	66	RH [%]
Inspector:	Alain Zoller	960	[hPA]
		0.1	Wind [m/s]

Shock loading test result ⁽¹⁾

Weak link used [daN]: **1000**
 Visual inspection: **No visible damage** Results: **POSITIVE**
 Uncertainty k=2 [%] ⁽²⁾ **10**

Weak link



Instruments	Validity	Manufacturer	s/n
Weak link	2020	Tost	n/a
Cable	2020	Rotex	n/a
Geos n° 11 Skywatch	08.05.2019	JDC elec.	22

Inspection certificate number: **PG_1318.2018**


Sustained loading test results ⁽³⁾

Result : **POSITIVE**
Calculated max load value with 3 sec or five peaks [kg] : **120.63**

Required sustained loading test results ⁽⁴⁾

Required load value for 3s at 8g [N] : **9025.20**
Required load value for 5 peaks at 10g [N] : **11281.50**
Required load value for 3s at 8g includes uncertainty [N] : **9076.06**
Required load value for 5 peaks at 10g includes uncertainty [N] : **11332.36**
Uncertainty K=2 [%] : **0.487**

Graphic sustained loading diagram





Inspection certificate number: **PG_1318.2018**

Detailed sustained loading test results

Calculated cumulative duration at max load [s] : **3.5**

Calculated max load value duration of 3 sec. [N] : **1183.39**

Calculated max load value duration of 3 sec. [kg] : **120.63**

Calculated max load value with five peaks [N] : **n/a**

Calculated max load value with five peaks [kg] : **n/a**

Calculated max load value with 3 sec or five peaks [N] : **1183.39**

Calculated max load value with 3 sec or five peaks [kg] : **120.63**

Instruments	Manufacturer	Type nr.	S/N
Load sensor	HBM	1-S9M/50KN-1	31314652
Geos n°11 Skywatch	JDC	Geos n° 11	0022

The validation of this test report is given by the signature of the test manager on inspection certificate 71.8.1

Air Turquoise SA has thoroughly tested the sample of paraglider mentioned above and certifies its conformity with the standards **EN 926-1:2015 chapter 4.4, 4.5 | LTF NFL II-91/09 chapter 3**

(1) The paraglider is subjected to a shock load . Shock load is limited using a weak link according to the weight range of glider. The weak link breaks or 5 s has elapsed since the start of the shock load. The wing is then visually inspected for damage.

(2) Weak link value include the uncertainty for weight range test values / The uncertainty state is the expanded uncertainty obtained by multiplying the standard uncertainty by the coverage factor $k = 2$. The value of the measurand lies within the assigned range of values with a probability of 95%.

(3) The test specimen (sample) is attached to the electronic sensors on the tow vehicle.

A controller is positioned on the tow vehicle in order to operate the paraglider control lines to stabilize the wing.

The speed of the vehicle is increased as gradually as possible, enabling the controller to obtain satisfactory stabilisation of the flight path of the paraglider.

When the paraglider has stabilized, the speed is increased gradually until either:

- a) the measured load exceeds a load factor of eight times the maximum total weight in flight recommended by the manufacturer, for a minimum cumulative duration of 3 s; or
- b) five peaks separated by at least 0,3 s are obtained above ten times the maximum total weight in flight recommended by the manufacturer, in one run.

(4) The calculated value include the value minus the uncertainty / The uncertainty stated is the expanded uncertainty obtained by multiplying the standard uncertainty by the coverage factor $k = 2$. The value of the measurand lies within the assigned range of values with a probability of 95%.